

**In the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1-10. (CANCELED)

11. (NEW) An interior finish building material comprising a gypsum-base building material composition for an interior finish, the composition containing from 1% by weight to 25% by weight of at least one naturally occurring zeolite.

12. (NEW) The building material of claim 11 wherein the composition contains at least 5% by weight of the zeolite.

13. (NEW) The building material of claim 11 wherein the composition contains at least 10% by weight of the zeolite

14. (NEW) The building material of claim 11 wherein the composition contains from 5% by weight to 20% by weight of the zeolite

15. (NEW) The building material of claim 11 wherein the composition contains from 10% by weight to 15% by weight of the zeolite

16. (NEW) The building material of claim 11 wherein said building material is a building board or a plaster.

17. (NEW) The building material of claim 11 wherein said zeolite has a grain size of  $\leq 200 \mu\text{m}$ .

18. (NEW) The building material of claim 11 wherein said zeolite has a grain size of  $\leq 150 \mu\text{m}$

19. (NEW) The building material of claim 11 wherein said zeolite has a  $d_{50}$  value of from  $30 \mu\text{m}$  to  $90 \mu\text{m}$ .

20. (NEW) The building material of claim 11 wherein said zeolite has a  $d_{50}$  value of from  $40 \mu\text{m}$  to  $70 \mu\text{m}$ .

21. (NEW) The building material of claim 11 wherein said zeolite has a mineral phase composition selected from the group consisting of clinoptilolite, heulandite, chabasite, phillipsite, morderite and mixtures thereof.

22. (NEW) The building material of claim 11 wherein said zeolite is employed in a native form.

23. (NEW) The building material of claim 11 wherein the gypsum content is at least 30% by weight.

24. (NEW) The building material of claim 11 wherein the gypsum content is at least 50% by weight.

25. (NEW) The building material of claim 11 wherein the gypsum content is at least 70% by weight.
26. (NEW) The building material of claim 11 wherein the zeolite has an oil number of at most 25 g/100 g of zeolite.
27. (NEW) The building material of claim 11 wherein the zeolite has an oil number of at most 10 g/100 g of zeolite.
28. (NEW) The building material of claim 11 having less than 3% diatomaceous earth.
29. (NEW) The building material of claim 11 wherein the zeolites are not admixed with antibacterial cations.
30. (NEW) The building material of claim 11 wherein the zeolites are mixed with stucco.
31. (NEW) A method of using the building material of claim 11 to reduce airborne pollutants in interiors.
32. (NEW) The method of claim 31 wherein said airborne pollutants are selected from the group consisting of formaldehyde, benzene, ammonia, tobacco smoke and mixtures thereof.

33. (NEW) The building material of claim 11 characterized by being sandwich-type plaster boards or gypsum boards coated with a glass fiber web and optionally being perforated.

34. (NEW) The building material of claim 11 characterized by being a plaster in which calcium sulfate semihydrate is used as a binder.